

TABLE 1005-1 AGGREGATE GRADATION, COARSE AGGREGATE																		
STD. SIZE #	PERCENTAGE OF TOTAL BY WEIGHT OF PASSING (mm sieve)																REMARKS	
	2" (50.0)	1 1/2" (37.5)	1" (25.0)	3/4" (19.0)	1/2" (12.5)	3/8" (9.5)	#4 (4.75)	#8 (2.36)	#10 (2.00)	#16 (1.18)	#30 (0.600)	#40 (0.425)	#50 (0.300)	#80 (0.180)	#100 (0.150)	#200 (0.075)		
4	100	90-100	20-55	0-15		0-5											0- 0.6	Asphalt Plant Mix Pavement
467M	100	95-100		35-70		0-30	0-5										0- 0.6	Asphalt Plant Mix Pavement
5		100	90-100	20-55	0-10	0-5											0- 0.6	AST Mat coat, Sediment Control Stone
57		100	95-100		25-60		0-10	0-5									0- 0.6	Str. Conc., Shldr. Drain, Sediment Control Stone
57M		100	95-100		25-45		0-10	0-5									0- 0.6	P. C. Concrete Pavement
6			100	90-100	20-55	0-15	0-5										*	AST
67			100	90-100		20-55	0-10	0-5									0- 0.6	Str. Conc., Asphalt Plant Mix Pvmt.
78M				100	98-100	75-100	20-45	0-15									0- 0.6	Asphalt Plant Mix Pvmt., AST Weep Hole Drains, Str. Concrete
14M						100	35-70	5-20		0-8							*	* AST
ABC		100	75-97		55-80		35-55		25-45			14-30					4-12**	Aggr. Stabilization Aggr/ Base Course Asph. Plant Mix Pvmt
ABC(M)		100	75-100		45- 79		20- 40		0- 25								0-12**	Maintenance Stabilization